













**TECHNICAL FEATURES  
CARATTERISTICHE TECNICHE  
TECHNISCHE DATEN  
CARACTERISTIQUES TECHNIQUES**

Product, Prodotto, Produkt, Produit: L'ALTRA PIETRA® MUSEO





Rev: 06/02/2018

FEATURE CARATTERISTICA DATEN CARACTÉRISTIQUE		TECHNICAL FEATURES CARATTERISTICHE TECNICHE TECHNISCHE DATEN CARACTÉRISTIQUES TECHNIQUES	STANDARD NORMA NORM NORME	ESTABLISHED LIMITS LIMITI PREVISTI VORGESEHENE GRENZWERTE LIMITES ÉTABLIES		L'ALTRA PIETRA®
<b>REGULARITY</b> REGOLARITÀ REGELMÄßIGKEIT RÉGULARITÉ		<b>LENGHT AND WIDTH</b> LUNGHEZZA E LARGHEZZA LÄNGE UND BREITE LONGUEUR ET LARGEUR	ISO 10545-2	± 0.6 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>THICKNESS</b> SPESSORE DICKE ÉPAISSEUR	ISO 10545-2	± 5.0 %	± 0.5 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>RECTANGULARITY</b> ORTOGONALITÀ RECHTWINKLIGKEIT PERPENDICULARITÉ	ISO 10545-2	± 0.5 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>STRAIGHTNESS OF SIDES</b> RETTILINEITÀ DEGLI SPIGOLI GERADLINIGKEIT DER KANTEN RECTITUDE DES ARETES	ISO 10545-2	± 0.5 %	± 1.5 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>SURFACE FLATNESS</b> PLANARITÀ EBENFLÄCHIGKEIT PLANEITÉ DE SURFACE	ISO 10545-2	± 0.5 %	± 2 mm	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
<b>STRUCTURAL</b> STRUTTURALE STRUKTURELL STRUCTURAL		<b>WATER ABSORPTION</b> ASSORBIMENTO D'ACQUA WASSERAUFNAHME ABSORPTION D'EAU	ISO 10545-3	≤ 0.5 %		<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
		<b>BREAKING STRENGHT</b> SFORZO DI ROTTURA BRUCHKRAFT FORCE DE RUPTURE	ISO 10545-4	≥ 1300 N		≥ 12000 N
		<b>MODULUS OF RUPTURE</b> MODULO DI ROTTURA BRUHLAST MODULE DE RUPTURE	ISO 10545-4	≥ 35 N/mm <sup>2</sup>		≥ 48 N/mm <sup>2</sup>
<b>SURFACE</b> SUPERFICIE OBERFLÄCHE SURFACE		<b>ABRASION RESISTANCE</b> RESISTENZA ALL'ABRASIONE ABRIEBFESTIGKEIT RESISTANCE A L'ABRASION	ISO 10545-6	≤ 175 mm <sup>3</sup>		<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
<b>THERMAL HYGROMETRIC</b> TERMO IGROMETRICHE THERMAL HYGROMETRISCH THERMIQUE HYGROMÉTRIQUE		<b>LINEAR THERMAL-EXPANSION</b> DILATAZIONE TERMICA LINEARE LINEARER WÄRMEAUSDEHNUNG DILATATION THERMIQUE LINEAIRE	ISO 10545-8	<b>VALUE DECLARED</b> VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE		α ≤ 7 · 10 <sup>-6</sup> °C
		<b>THERMAL SHOCK RESISTANCE</b> RESISTENZA AGLI SBALZI TERMICI WIDERSTANDSFÄHIGKEIT GEGEN TEMPERATURSCHWANKUNGEN RÉSISTANCE AUX ÉCARTS DE TEMPÉRATURE	ISO 10545-9	<b>TEST PASSED</b> TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>FROST RESISTANCE</b> RESISTENZA AL GELO FROSTBESTÄNDIGKEIT RÉSISTANCE AU GEL	ISO 10545-12	<b>TEST PASSED</b> TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>REACTION TO FIRE</b> REAZIONE AL FUOCO REAKTION ZUM FEUER RÉACTION AU FEU	EN 9239-1	<b>TEST PASSED</b> TEST SUPERATO TEST BESTANDEN TEST RÉUSSI		<b>A1fl</b>

**TECHNICAL FEATURES**  
**CARATTERISTICHE TECNICHE**  
**TECHNISCHE DATEN**  
**CARACTERISTIQUES TECHNIQUES**

Product, Prodotto, Produkt, Produit: L'ALTRA PIETRA<sup>®</sup> MUSEO

Rev: 06/02/2018

<b>LIGHT</b> LUCE LICHT LUMIÈRE		<b>COLOUR RESISTANCE TO LIGHT EXPOSURE</b> RESISTENZA DEI COLORI ALLA LUCE LICHTECHTHEIT DER FARBEN RÉSISTANCE DES COULEURS À LA LUMIÈRE	<b>DIN 51094</b>	<b>NO NOTICEABLE COLOUR MODIFICATIONS.</b> ASSENZA DI APPREZZABILI ALTERAZIONI DI COLORE. KEIN SICHTBARE FARBVERÄNDERUNGEN AUFWEISEN. AUCUN ALTÉRATIONS APPRÉCIABLES DE COULEUR.	<b>COMPLYING</b> CONFORME ERFÜLLT CONFORME
<b>CHEMICAL</b> CHIMICA CHEMISCH CHIMIQUE		<b>RESISTANCE TO CHEMICALS (ACIDS, BASES AND SALTS)</b> RESISTENZA ALL'ATTACCO CHIMICO (ACIDI, BASI E SALI) CHEMIKALIENBESTÄNDIGKEIT (SÄUREN, BASIS UND SALZ) RESISTANCE A L'ATTAQUE CHIMIQUE (ACIDES, BASES ET SELS)	<b>ISO 10545-13</b>	<b>UB MINIMUM</b> UB MINIMO UB MINIMUM UB MINIMUM	<b>UA ULA UHA</b> <b>GUARANTEED</b> GARANTITO GARANTIERT GARANTI
		<b>RESISTANCE TO STAINS</b> RESISTENZA ALLE MACCHIE FLECKENBESTÄNDIGKEIT RESISTANCE AUX TACHES	<b>ISO 10545-14</b>	<b>≥ 3</b>	<b>5 GUARANTEED</b> 5 GARANTITO 5 GARANTIERT 5 GARANTI
<b>SAFETY</b> SICUREZZA SICHERHEIT SÉCURITÉ		<b>SKID RESISTANCE</b> RESISTENZA ALLO SCIVOLAMENTO RUTSCHHEMMUNG RÉSISTANCE AU GLISSEMENT	<b>DIN 51130</b>	<b>VALUE DECLARED</b> VALORE DICHIARATO ERKLÄRTER WERT VALEUR DÉCLARÉE	<b>R11</b>
			<b>DIN 51097</b>		<b>A+B+C</b>

**Compliant with standards EN 14411 (ISO 13006) annex G group Bla**  
**Conforme alla norma EN 14411 (ISO 13006) Appendice G gruppo Bla**